

ATA AIRLINES, INC.

APPLY ANTI-CORR TO AFT FUSELAGE FAIRING AREA., RIGHT AND LEFT

PAGE 1 / 1

CHECK BEING PERFORMED: Custom

ZONES: 168 169
A/C NUMBER:
REV. DATE: 04/09/99
FREQUENCY: D

W/C NUMBER: 510L5312
DATE:
W/O:
JAC CODE:



MFR P/N	DESCRIPTION	QTY
AV30	ANTI-CORROSION COMPOUND	A/R

TOOLS	DESCRIPTION	QTY
C-53-160-05		

PANELS

168A
169A

MECH INSP

| APPLY CORROSION INHIBITOR COMPOUND

| WARNING: ALWAYS USE A RESPIRATOR WHEN PERFORMING SPRAY
| APPLICATIONS. DO NOT APPLY CORROSION PREVENTATIVE
| TO FIBERGLASS DUCTS, HOT AIR DUCTS, OXYGEN SYSTEMS,
| BEARINGS, INSULATION, PLUMBING OR ANY AREA WHERE THE
| TEMPERATURE NORMALLY EXCEEDS 220 DEGREES F TO PREVENT
| FIRE HAZARD.

| CAUTION: SURFACES MUST BE CLEAN AND DRY PRIOR TO CORROSION
| PREVENTATIVE APPLICATIONS. TO PREVENT DAMAGE, DO NOT
| APPLY CORROSION PREVENTATIVE ON CABLES, WIRES, OR
| PLASTIC. DRAIN HOLES AND GAPS MUST BE CLEAR OF
| OBSTRUCTIONS.

NOTE: REMOVAL OF R/H FAIRING 168A AND L/H FAIRING 169A IS
REQUIRED TO PERFORM THIS TASK.

| 1 APPLY SUITABLE APPROVED WATER DISPLACING/ANTI-CORROSION
| COMPOUND (AV30) TO THE FOLLOWING AREAS.

_____ 1 LEFT HAND SIDE, LOWER AFT FUSELAGE FAIRING AREA (ZONE 169).

_____ 2 RIGHT HAND SIDE, LOWER AFT FUSELAGE FAIRING AREA (ZONE 168)

*****End of Workcard*****