

CHECK BEING PERFORMED: Custom

ZONES: 316
A/C NUMBER:
REV. DATE: 06/22/06
FREQUENCY: 2C

W/C NUMBER: 531I5503
DATE:
W/O:
JAC CODE:



PANELS

316AB 316CB 317AB 317CB
316BB 316DB 317BB

REFERENCES

C-53-310-06 531I5503

MECH INSP

- XXXXX 1 CLEAN AFT PRESSURE BULKHEAD AREA, AFT SIDE, BELOW WL 200 (ZONE 316) AS REQUIRED TO PERFORM CORROSION INSPECTION.
2 VISUALLY INSPECT ALL THE FOLLOWING PRIMARY AND LISTED SECONDARY STRUCTURE FROM A DISTANCE CONSIDERED NECESSARY TO DETECT EARLY STAGES OF CORROSION. VISUALLY INSPECT ALL FUSELAGE FAILSAFE STRAPS AND LAP JOINTS FOR DISBONDING AND/OR CORROSION.

XXXXX A INSPECT AFT PRESSURE BULKHEAD AREA, AFT SIDE, BELOW WL 200 (ZONE 316) FOR CORROSION.

- 1 FOR CRACKS, PERMANENT DEFORMATION, OR CORROSION TO PRIMARY STRUCTURE (REF. SRM CHAPTER 51); INITIATE A SERVICE DIFFICULTY REPORT (SDR) (REF. GMM, CHAPTERS 4, 12, AND 16) AND RECORD THE ASSOCIATED NON-ROUTINE NUMBERS BELOW.

Four horizontal lines for data entry.

WARNING: ALWAYS USE A RESPIRATOR WHEN PERFORMING SPRAY APPLICATIONS. DO NOT APPLY DINITROL TO FIBERGLASS DUCTS, OXYGEN SYSTEMS, BEARINGS, INSULATION, PLUMBING OR ANY AREA WHERE THE TEMPERATURE NORMALLY EXCEEDS 220 DEGREES F TO PREVENT FIRE HAZARD.

CAUTION: SURFACE MUST BE CLEAN AND DRY PRIOR TO DINITROL APPLICATION. TO PREVENT DAMAGE, DO NOT APPLY DINITROL ON CABLES, PULLEYS, WIRING, OR PLASTICS. DRAIN HOLES AND GAPS MUST BE CLEAR.

- 3 APPLY APPROVED WATER DISPLACING/ANTI-CORROSION COMPOUND (AV30 CCN 9200544) TO AFT PRESSURE BULKHEAD AREA, AFT SIDE, BELOW WL 200 (ZONE 316).

PRESSURE BULKHEAD AREA

PAGE:2 /2

A/C NUMBER:

CHECK BEING PERFORMED: Cust

W/C NUMBER: 531I5503 (continued)

MECH: INSP:

NOTE: IF INHIBITOR WAS REMOVED FOR INSPECTION, FULL
REAPPLICATION IS REQUIRED. IF INHIBITOR WAS NOT REMOVED,
REAPPLY ONLY TO THE JOINTS AND SEAMS.

XXXXX 4 CLEAR ANY BLOCKED HOLES OR GAPS THAT MAY HINDER DRAINAGE
WITHOUT REMOVING THE REQUIRED AMOUNT OF DINATROL APPLICATION.

*****END OF WORKCARD*****